## **DUROMER**

## **DURALAC A65ABK804**

## **DESCRIPTION**

Duralac A65ABK804 is a flame retarded ABS injection moulding compound coloured black.

## PROCESSING CONDITIONS

| TEMPERATURES       |               |
|--------------------|---------------|
| Drying             | 82℃ 2 hours   |
| Rear zone          | 180 – 200℃    |
| Middle zone        | 190 – 210℃    |
| Front zone         | 190 – 220℃    |
| Melt temperature   | 190 – 230℃    |
| Mould temperature  | 40 – 70℃      |
| PRESSURES          |               |
| Injection pressure | 70 – 100 MPa  |
| Hold pressure      | 35 – 70 MPa   |
| Back pressure      | 0.3 – 0.7 MPa |
| SPEEDS             |               |
| Fill speed         | 25 – 50 mm/s  |
| Screw speed        | 60 – 90 RPM   |
| DRYING             |               |
|                    |               |

80℃ for 2-3 hours.

Duromer Products Pty Ltd PO Box 3070 Rhodes NSW 2138 Ph +61 2 97430355 Fax +61 2 97430273

| TYPICAL PROPERTIES           |      |                |  |
|------------------------------|------|----------------|--|
|                              | DAM  | Test<br>Method |  |
|                              |      |                |  |
| MECHANICAL                   |      |                |  |
| Tensile Strength, Yield MPa  | 39   | ISO-527        |  |
| Flexural Strength, MPa       | 48   | ISO-178        |  |
| Flexural Modulus, MPa        | 2000 | ISO-178        |  |
| Charpy Impact, notched kJ/m² | 8.50 | ISO-179        |  |
|                              |      |                |  |
| Specific Gravity             | 1.17 | D-792          |  |
| THERMAL                      |      |                |  |
| Flammability* UL94 2.2mm     | V-0  | UL94           |  |

These values are for natural colour resins only. The data listed here fall within the normal range of product properties, but they should not be used to establish specification limits nor used alone as the basis of design.

DISCLAIMER: Except as provided below, all express and implied warranties, guarantees and conditions said to arise in respect of information supplied by Duromer Products Pty Ltd or otherwise under statute or general law as to merchantability, description, quality, suitability or fitness of the goods for any purpose or as to design, assembly, installation, materials or workmanship or otherwise are hereby expressly excluded and Duromer Products Pty Ltd shall not be liable for physical or financial injury, loss or damage or for consequential loss or damage of any kind arising out of the supply, preparation, production, installation, performance or operation of the goods or arising out of Duromer Products Pty Ltd's negligence or in any way whatsoever. The liability of Duromer Products Pty Ltd for a breach of a condition or warranty implied by Div 2 of Pt V of the Trade Practices Act of 1974 is not excluded or restricted but is (other than S.69) hereby limited to:- (a) the replacement of the goods or the supply of equivalent goods; (b) the repair of goods; (c) the payment of the cost of replacing the goods or of acquiring equivalent goods; (d) the payment of the cost of having the goods repaired. Freedom from patent rights must not be assumed.

<sup>\*</sup> Do not leave this material in the barrel for extended periods.